





10mm COMFORT

DIN 51130 R10

BS 7976-2 Av.DRY 60 PTV

BS 7976-2 Av.WET 44 PTV




10mm DREAM

DIN 51130 R11

BS 7976-2 Av.DRY 64 PTV

BS 7976-2 Av.WET 55 PTV



10mm ELEGANCE

DIN 51130 R10

BS 7976-2 Av.DRY 61 PTV

BS 7976-2 Av.WET 43 PTV



10mm SECRET

DIN 51130 R11

BS 7976-2 Av.DRY 62 PTV

BS 7976-2 Av.WET 51 PTV

- Tested to UK and European Standards
- Toughened and laminated
- Multi-laminated with Vanceva Coloured Interlays
- Can be processed or shaped as required
- Patterns are obscure all over




10mm TRUST

DIN 51130 R11

BS 7976-2 Av.DRY 62 PTV

BS 7976-2 Av.WET 47 PTV


- GLASS FLOORS
- INTERNAL AND EXTERNAL OPTIONS
- PTV = PENDULUM TEST VALUE



10mm COMFORT SANDBLAST

BS 7976-2 Av.DRY 65 PTV

BS 7976-2 Av.WET 61 PTV



SANDBLAST

BS 7976-2 Av.DRY 65 PTV

BS 7976-2 Av.WET 59 PTV

CAN BE APPLIED TO ANY GLASS THICKNESS



AVANT GARDE

BS 7976-2 Av.DRY 72 PTV

BS 7976-2 Av.WET 61 PTV

CAN BE APPLIED TO ANY GLASS THICKNESS